


Attorney's Docket: 2000FR303
Serial No.: 09/821,876
Art Unit 1711

Amendments to the Claims

1. (currently amended) Fluid silico-acrylic compositions, stable in the long term, polymerizable thermally and by radiation, by mechanism giving rise to free radicals, with a very low water (~~below 1%~~) and volatile solvent content, containing silica, a silane and a multifunctional acrylic monomer, wherein the silica is in the form of individualised particles with an average diameter in the range 9 to 100 nm, not interconnected by siloxane bonds, and the silane is a vinyl silane of the formula (I)



in which R represents a methyl or ethyl radical, and the multifunctional (meth)acrylic monomer is an alkoxyated (meth)acrylate not soluble in water, where the fluid silico-acrylic compositions have a Brookfield viscosity after manufacture below 1500 mPa.s.

2. (previously presented) Compositions according to claim 1, where said composition contain 5 to 60 wt.% silica.

3. (previously presented) Compositions according to claim 2, where said composition contain 30 to 50 wt.% silica.

4. (previously presented) Compositions according to claim 1, where said composition contain silica in the form of individualised particles, not interconnected by siloxane bonds, with an average diameter in the range 12 to 50 nm.

Attorney's Docket: 2000FR303
Serial No.: 09/821,876
Art Unit 1711

5. (previously presented) Compositions according to claim 1, where the quantity of vinyl silane of formula (I) is within the range 0.01 g to 1 g per gram initial dry silica.

6. (previously presented) Compositions according to claim 1, where the quantity of vinyl silane of formula (I) is within the range 0.05 g to 0.7 g per gram initial dry silica.

7. (previously presented) Compositions according to claim 1, where the multifunctional (meth)acrylic monomer of alkoxyated (meth)acrylate is ethoxylated or propoxylated di(meth)acrylate.

8. (previously presented) Compositions according to claim 1, where the multifunctional (meth)acrylic monomer of alkoxyated (meth)acrylate is ethoxylated or propoxylated tri(meth)acrylate.

9. (previously presented) Compositions according to claim 8, where the ethoxylated triacrylate monomer is the ethoxylated trimethylolpropane triacrylate.

10. (previously presented) Compositions according to claim 8, where the ethoxylated triacrylate monomer is the ethoxylated pentaerythritol triacrylate.

11. (previously presented) Compositions according to claim 1, where the multifunctional (meth)acrylic monomer of alkoxyated (meth)acrylate is ethoxylated or propoxylated tetra (meth)acrylate.

12. (currently amended) Method for preparation of a composition as defined in claim 1, comprising the steps of:

Attorney's Docket: 2000FR303
Serial No.: 09/821,876
Art Unit 1711

mixing, at ambient temperature under agitation, an aqueous solution of said silica, said vinylsilane of formula (I), said alkoxyated (meth)acrylate, and isopropyl alcohol; and

distilling the resultant mixture under reduced pressure and under agitation, at a temperature below 50°C, until the so that the quantity of residual water is below 1% and volatile solvents are eliminated.

13. (previously presented) Method according to claim 12, where the initial aqueous silica sol is an acid sol.

14. (previously presented) Method according to claim 13, where the initial silica sol has a pH between 1 and 3.

15. (currently amended) A method of providing a transparent and uncoloured ~~coatings~~ coating on a substrate to protect said substrate against abrasion comprising the steps of:

providing a substrate;

depositing a coating composition to said substrate, where said coating composition is the composition of claim 1 ; and

hardening said coating composition.

16. (currently amended) A method of providing a transparent and uncoloured ~~varnishes~~ varnish on a substrate to protect said substrate against scratch comprising the steps of:

providing a substrate;

depositing a coating composition to said substrate, where said coating composition is the composition of claim 1 ; and

hardening said coating composition.

Attorney's Docket: 2000ER303
Serial No.: 09/821,876
Art Unit 1711

17. (previously presented) A method according to claim 15, where hardening said coating composition is done thermally or/and by radiation, by a radical mechanism.

18. (previously presented) A method according to claim 16, where hardening said coating composition is done thermally or/and by radiation, by a radical mechanism.

19. (new) Compositions according to claim 1, wherein the low water content is below 1%.